

### Recommended Polishes Chart

CHO: Chromium Oxide | CMO: Cerium Oxide | DIA: Diamond | LA: Linde A | TO: Tin Oxide

Stone	CHO	CMO	DIA	LA	TO	Stone	CHO	CMO	DIA	LA	TO
Actinolite					X	Labradorite					X
Agate		X			X	Lapis Lazuli	X			X	X
Alabaster					X	Limestone	X	X		X	X
Amazonite					X	Lapidolite	X				
Amber					X	Malachite	X			X	X
Amblygonite					X	Moonstone					X
Andalusite					X	Nephrite	X			X	X
Apatite	X			X		Obsidian	X				X
Aventurine	X				X	Onyx	X	X			X
Azurite	X				X	Opal	X	X			X
Apophyllite	X					Peridot			X	X	X
Aragonite					X	Petrified	X	X		X	X
Axinite	X					Phenacite					X
Barite	X					Pollucite		X			
Benitoite		X				Quartz		X			X
Beryl		X	X		X	Rhodochrosite	X			X	X
Bloodstone				X		Rhodonite	X	X			X
Brazilianite					X	Ruby			X		
Calcite	X				X	Rutile				X	
Cassiterite					X	Sapphire			X		
Celestite	X					Scapolite		X			
Cerussite	X					Scheelite	X				
Chrysoberyl			X			Serpentine	X			X	X
Coral					X	Smithsonite					X
Corundum			X			Sodalite		X			
Danburite					X	Sosolite	X				
Datolite					X	Spinel			X	X	X
Diopside	X					Sphalerite	X				
Diopase		X				Spodumene					X
Diorite	X	X		X	X	Sunstone					X
Enstatite					X	Thompsonite		X			
Epidote					X	Tiger-eye		X		X	X
Euclase					X	Titanite (Spene)					X
Feldspar		X			X	Topaz			X	X	X
Fluorite	X				X	Tourmaline			X	X	X
Garnet	X	X	X	X	X	Turquoise		X		X	X
Goldstone		X			X	Unikite		X			
Hematite		X				Varicite		X		X	X
Hickoryite				X		Vesuvianite		X			
Howlite	X	X		X	X	Williamsite				X	
Hypersthene					X	Wonderstone				X	X
Jadite	X	X		X	X	Wulfenite	X				
Jasper	X	X		X	X	Zircon					X
Kyanite					X	Zoisite		X			